

DUPONT™ NOMEX® LAMINATE TYPE NMN

TECHNICAL DATA SHEET

Product description

NOMEX® Laminate Type NMN is a triplex laminate constructed of calendered NOMEX® paper bonded to polyester film with a proprietary high temperature adhesive system. This laminate is designed not to delaminate or blister at high temperatures.

The polyester film in this three-ply laminate contributes high dielectric strength, as well as good initial tear strength and tensile properties.

The calendered NOMEX® paper provides long-term thermal stability, as well as improved propagation tear strengths.

Application

This laminate is broadly used in the manufacture and remanufacture of motors and generators of many sizes and temperature classes. The most important applications are for slot liners, wedges and phase insulation in Class H motors and generators, as well as in large and specialty Class F motors. Motor manufacturers as well as motor repair facilities who remanufacture motors like the ability to standardize on Type NMN, and use just one insulation material for all motors.

There are a number of insulation systems recognized by Underwriters Laboratories (UL), which include this laminate for both Class F and Class H motors. Upon request, access to these insulation systems is available from DuPont.

Case histories

Case histories detailing the use of Type NMN in motors and generators are available upon request.

PRODUCT DATA

| Product | ASTM D374 Thickness Nominal (inches) | Product Yield (yd ² /lb) (lb/yd ²) | | ASTM D149 Dielectric Strength (volts) | ASTM D257 Volume Resistivity (ohms-cm) | ASTM D257 Surface Resistivity (ohms/square) | ASTM D882 MD Tensile Strength (lb/in width) | ASTM D882 XD Tensile Strength (lb/in width) | ASTM D1004 MD Tear Strength (lbs) | ASTM D1004 XD Tear Strength (lbs) |
|------------|--------------------------------------|---|------|---------------------------------------|--|---|---|---|-----------------------------------|-----------------------------------|
| NMN 2-2-2 | 0.007 | 3.08 | 0.32 | 11,000 | 10 ¹⁵ | 10 ¹⁵ | 95 | 70 | 9 | 7 |
| NMN 2-5-2 | 0.010 | 1.92 | 0.52 | 16,000 | 10 ¹⁵ | 10 ¹⁵ | 115 | 145 | 18 | 12 |
| NMN 2-7½-2 | 0.012 | 1.49 | 0.67 | 18,000 | 10 ¹⁵ | 10 ¹⁵ | 200 | 180 | 25 | 20 |
| NMN 3-3-3 | 0.010 | 2.04 | 0.49 | 13,000 | 10 ¹⁵ | 10 ¹⁵ | 170 | 110 | 17 | 10 |
| NMN 3-5-3 | 0.012 | 1.64 | 0.61 | 17,000 | 10 ¹⁵ | 10 ¹⁵ | 175 | 150 | 26 | 18 |
| NMN 3-7½-3 | 0.014 | 1.28 | 0.78 | 19,500 | 10 ¹⁵ | 10 ¹⁵ | 210 | 175 | 30 | 22 |
| NMN 3-10-3 | 0.017 | 1.03 | 0.97 | 21,000 | 10 ¹⁵ | 10 ¹⁵ | 250 | 210 | 33 | 27 |
| NMN 3-14-3 | 0.021 | 0.91 | 1.10 | 32,000 | 10 ¹⁵ | 10 ¹⁵ | 314 | 213 | 45 | 41 |
| NMN 5-3-5 | 0.013 | 1.52 | 0.66 | 16,000 | 10 ¹⁵ | 10 ¹⁵ | 185 | 145 | 24 | 16 |
| NMN 5-5-5 | 0.016 | 1.25 | 0.80 | 19,000 | 10 ¹⁵ | 10 ¹⁵ | 200 | 170 | 28 | 19 |
| NMN 5-10-5 | 0.021 | 0.89 | 1.12 | 22,000 | 10 ¹⁵ | 10 ¹⁵ | 275 | 235 | 35 | 31 |



Specifications

The properties shown in this data sheet are typical values, and should not be used as specification limits. Contact DuPont for assistance in preparing specifications of these materials for your application.

Shelf life

The shelf life of NOMEX® laminates is in excess of one year when they are stored at or below room temperature.

Safety precautions

A Material Safety Data Sheet (MSDS) describing the use of this product is available upon request from DuPont.

Availability

DuPont™ NOMEX® Laminate, Type NMN is available from Von Roll Isola USA, DuPont's authorized sales agent, or from your local authorized distributor. For the name of a local fabricator or distributor, or for more information on this product, contact Von Roll Isola.

USA

DuPont
Advanced Fibers Systems
5401 Jefferson Davis Highway
Richmond, VA 23234
Tel: (800) 453-8527 (804) 383-4400
Fax: (800) 787-7086 (804) 383-4132
E-mail: afscdt@usa.dupont.com

Von Roll Isola USA, Inc.
One West Campbell Road
Schenectady, NY 12306
Tel: (800) 654-7652 (press 4)
(518) 344-7237
Fax: (518) 344-7384
Email: dupontlaminates@vonroll-isola.com
Website: www.vonrollisola.com



CANADA

DuPont Canada, Inc.
Advanced Fibers Systems
P. O. Box 2200
Streetsville Postal Station
Mississauga, Ontario, L5M 2H3
Canada
Tel: (800) 387-2122 (905) 821-5193
Fax: (905) 821-5177
E-mail: products@can.dupont.com

Product safety information is available upon request.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentations. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DUPONT MAKES NO WARRANTIES AND ASSUMES NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

H-93490 10/02

